

Bituthene® 6000 EIM

Heavy duty, preformed composite membrane combining a self-adhesive rubber/bitumen compound and a tough, puncture-resistant four-ply polyethylene laminate for electrical insulation in critical sub-structures and civil works

Product Description

Bituthene® 6000 EIM, whilst designed as a waterproofing membrane for concrete structures, possesses excellent electrical insulation properties. Bituthene is composed of a tough, cross-laminated polyethylene film, backed by a self-adhesive rubberised asphalt compound, all of which components provide high resistance to the passage of direct or alternating current.

Features

- Cross-laminated film — provides dimensional stability, high tear strength and puncture resistance.
- Cold applied — no heating, hot mopping or torches.
- Flexible — retains flexibility to accommodate ground movement, structural movements.
- Controlled thickness — factory controlled uniform thickness.
- Chemically-resistant.
- Simple, reliable, low labour cost installation.

Bituthene 6000 EIM is composed of 1.4mm of rubberised asphalt compound and 0.2mm, 4 ply cross-laminated polyethylene providing superior puncture and damage resistance. It is important to ensure that the membrane resists damage during installation, and during subsequent construction activities, to provide a continuous barrier to the passage of current. The self-adhesive compound allows easy and safe cold application over large areas, without the need for torching or hot mopping of asphaltic compounds. This is particularly important when work is being carried out in confined spaces or underground, on, for example Mass Transit Rail Station Platforms.

Double layer of Bituthene 6000 EIM enables electrical resistivity of up to 6000×10^{11} ohm-cm.

Installation

Concrete surfaces shall be dry, free of loose debris and sharp protrusions and hollows. An application of WP-3000 water-based primer is recommended, at the rate of 12 to 15m² / litre. A water-based primer is recommended, for safety reasons, when working in enclosed spaces underground. The primer is allowed to dry completely before application of the membrane.



Supply

Bituthene 6000 EIM	1m x 20m roll (20 sq m) Average net weight 40kg
Storage	Store upright in dry conditions below 35 °C
Primer WP-3000	18.9 litre pails
Coverage	12 - 15 sq m / litre depending on method of application, surface texture, porosity and ambient temperature
Bituthene LM	5.7 litre pails
Bituthene Mastic	850cc cartridges, 3 litre pails
Bituthene Lap Roller	Unit

Performance

Property	Typical Values	Test Method
Nominal Thickness*	3.2mm	NA
Elongation	min. 300%	ASTM D412 Modified
Tensile Strength	min. 5000Kpa	ASTM D412 Modified
Volume/Electrical resistivity	min. 5000 x 10 ¹¹ ohm-cm	ASTM D-257

Typical test values represent average values from samples tested. Test methods noted may be modified.

* Nominal thickness refers to the thickness of the membrane without release liner.

For complete instructions on the application of Bituthene membranes, please refer to our general data sheets and contractor guide, available from your local GCP representative.

Quality Assurance

GCP Applied Technologies is certified to ISO 9002 by TUV SUD PSB Pte Ltd.

Health and Safety

Refer to relevant Material Health and Safety data sheets.

Specification

Bituthene 6000 EIM preformed membrane shall be applied onto smooth primed concrete by applying the preformed membrane, sticky side downwards to give well rolled 50mm overlaps, laid

strictly in accordance with manufacturer's instructions and supplied by GCP Applied Technologies. For further information, contact your local GCP representative.

Guarantee

Bituthene products are warranted to be free of defects in manufacture for a period of ten years.

Technical Services

For assistance with working drawings for projects and additional technical advice, please contact GCP Applied Technologies.

gcpat.com | For technical information: asia.enq@gcpat.com

Australia 1800 855 525 New Zealand +64 9 448 1146 China Mainland +86 21 3158 2888 Hong Kong +852 2675 7898
India +91 124 488 5900 Indonesia +62 21 893 4260 Japan +81 3 5226 0231 Korea +82 32 820 0800 Malaysia +60 3 9074 6133
Philippines +63 49 549 7373 Singapore +65 6265 3033 Thailand +66 2 709 4470 Vietnam +84 8 3710 6168

We hope the information here will be helpful. It is based on data and knowledge considered to be true and accurate, and is offered for consideration, investigation and verification by the user, but we do not warrant the results to be obtained. Please read all statements, recommendations, and suggestions in conjunction with our conditions of sale, which apply to all goods supplied by us. No statement, recommendation, or suggestion is intended for any use that would infringe any patent, copyright, or other third party right.

Bituthene is a trademark, which may be registered in the United States and/or other countries, of GCP Applied Technologies, Inc. This trademark list has been compiled using available published information as of the publication date and may not accurately reflect current trademark ownership or status.

© Copyright 2016 GCP Applied Technologies, Inc. All rights reserved.

GCP Applied Technologies Inc., 62 Whittemore Avenue, Cambridge, MA 02140, USA

Printed in Singapore | 03/16 | 300-Bituthene-3



gcp applied technologies